

BASE OIL SN-150

CHARACTERISTICS:

Base oil SN-150 is produced from vacuum fractions of crude oil, selectively refined, dewaxed by means of solvents and hydro-refined.

APPLICATION:

Base oil SN-150 is intended for use in production of lubricants.

PHYSICAL AND CHEMICAL PROPERTIES:

PROPERTY	UNIT	MINIMUM VALUE	MAXIMUM VALUE	TYPICAL VALUE	TEST METHOD
Density at 20 °C	g/cm ³	0,860	0,875	0,873	PN-EN ISO 3675
Kinematic viscosity at 40°C	mm ² /s	28,8	33,5	31,4	PN-EN ISO 3140
Kinematic viscosity at 100°C	mm ² /s	5,0	5,5	5,23	PN-EN ISO 3140
Viscosity index	-	95	-	95	PN-79/C-04013
Pour point	°C	-	-12	-12	PN-ISO 3016
Flash point (open cup).	°C	210	-	220	PN-EN ISO 2592
Flash point (closed cup)	°C	190	-	215	PN-EN ISO 2719
Coking residue (Conradson)	%(m/m)	-	0,03	0,01	PN-85/C-04075
Ash residue	%(m/m)	-	0,005	0,001	PN-EN ISO 6245
Basic number	mgKOH/g	-	0,05	0,01	PN-85/C-04066
Volatiles content (Noack), % (1h/250°C)	%(m/m)	-	18,5	14,0	PN-C-04124
Colour	-	-	1,0	0,5	ASTM D 1500
Demulsibility 54°C, time to Oil-water emulsion separation	min	-	20	5	PN-86/C-04065
Refractive index n _D ²⁰	-	-	-	1,4815	PN-81/C-04952
Viscosity – gravity constant (VGC)	-	-	-	0,821	ASTM D 2140
Carbon-type composition					
- C _A	%	-	-	6,5	ASTM D 2140
- C _N				32,5	
- C _P				61,0	
Groups composition:					
- saturated hydrocarbons	%(m/m)	-	-	73,2	ASTM D 2007
- aromatic hydrocarbons				26,2	
- resins				0,6	
Sulphur content	%(m/m)	-	-	0,45	PN-EN ISO 8754
Air release	min	-	-	3	ASTM D 3427
Polycyclic aromatics content	%(m/m)	-	3,0	0,9	IP 346

Note: Actual values are placed in quality certificates attached to each delivery.

PACKAGES: BULK

MADAK TRADE S.R.O.

sídlem: Nádražní 207/17, Český Těšín, PSČ 737 01, DIČ: CZ28608071,
společnost zapsaná v obchodní rejstříku vedeném Krajským soudem v Ostravě, oddíl C, číslo vložky: 34395
www.madaktrade.cz, office@madaktrade.cz